

Ruby 70 Acoustic

Datasheet

Classification	Norm	Tarkett Value
Product type	EN 651	Polyvinyl chloride floor coverings with foam layer
Commercial classification	ISO 10874	34 Very Heavy
Technical Characteristics	Norm	Tarkett Value
Total thickness	ISO 24346	3 mm
Wear layer thickness	ISO 24340	0,70 mm
Total weight	ISO 23997	2500 g/m ²
Surface treatment		Top Clean
Installation method		Glue-Down
Performance for CE Marking	Norm	Tarkett Value
Declaration of Performance #	EN 14041	0131-0056-DoP-2015-01
Reaction to fire	EN ISO 13501-1	Cfl-s1
Static Electrical Propensity	EN 1815	Antistatic (≤ 2 kV)
Thermal resistance	EN ISO 10456	0,040 m ² •K/W
Slip resistance	EN 13893	Class DS ($\mu \geq 0,30$)
Technical Performance	Norm	Tarkett Value
Residual indentation	EN ISO 24343-1	Required value: $\leq 0,20$ mm
Dimensional stability	EN ISO 23999	Average measured value : ≤ 0.10 %
Impact sound reduction - ΔL_w	EN ISO 717/2	19 dB
Reduction of in-room impact noise	NF S31-074	Class A (≤ 65 dB)
Slip resistance	DIN 51130	R10
Furniture leg	EN ISO 16581	No damage
Castor chair	EN ISO 4918	No damage
Curly resultant to heat	EN ISO 23999	$\leq 8 $ mm
Colour fastness to light	EN ISO 105-B02	≥ 6
Chemical resistance	EN ISO 26987	Not affected
Underfloor heating		Suitable (subfloor temperature maximum 27°C)
Sustainability performances	Norm	Tarkett Value
Recyclability through ReStart®		Recyclable
Carbon Footprint (Cradle-to-Gate, EPD Modules A1-A3)		8,69 kg CO ₂ eq /m ²
Total VOC Emissions	EN 16516	Gold (≤ 100 μ g / m ³)
Dimensions and designs		
Roll		Roll 2 x 23 m
Number of designs available		19



The above information is subject to modification for the benefit of further improvement (05/09/2023). According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website <https://www.tarkett.com>. Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.